UNITED STATES PATENT AND TRADEMARK OFFICE

CERTIFICATE OF CORRECTION

PATENT NO. : 7,344,655 B1
APPLICATION NO. : 10/049816
DATED : March 18, 2008
INVENTOR(S) : Mikito Nishii et al.

It is certified that error appears in the above-identified patent and that said Letters Patent is hereby corrected as shown below:

The drawing consisting of figure 2, should be deleted to appear as per attached figure 2.

Signed and Sealed this

Sixteenth Day of June, 2009

John Doll

JOHN DOLL
Acting Director of the United States Patent and Trademark Office

Fig. 2

	Ex. 1	Ex. 2	Ex. 3	Ex. 4	Ex. 5	Ex. 6	Ex. 7	Ex. 8	Ex. 9	Comparative Ex. 1	Comparative Ex. 2	Comparative Ex. 3	Comparative Ex. 4	Comparative Ex. 5	Comparative Ex. 6
Electric conductivity (μS/cm)	29.0	5.0	2.1	3.3	3.0	3.5	5.0	3.2	4.4	5850	3.5	1.8	1.8	286	0.88
Metal corrosion resistance Air n=2 Quantity of corrosion of Al(mg/cm²)	0.01	-0.04	0.04	-0.02	-0.02	-0.03	0.00	--	--	-0.02	-0.12	-0.12	--	-0.52	0.10
	-0.01	-0.04	0.15	0.01	-0.02	-0.01	-0.02	--	--	-0.03	-0.10	-0.09	--	-0.43	0.10
Metal corrosion resistance N_2 n=2 Quantity of corrosion of Al(mg/cm²)	0.00	--	0.04	--	--	--	--	--	--	--	--	0.02	--	--	--
	-0.01	--	0.05	--	--	--	--	--	--	--	--	0.04	--	--	--
Passivation current density N_2 (μA/cm²)	4.8	11	2.4	(7)	(15)	(18)	(18)	(80)	(80)	3.0	(100)	(100)	(100)	78	-
Passivation current density Air (μA/cm²)	2.4	12	2.4	--	--	--	--	--	--	3.0	2.0	1.3	--	210	-
Freezing point (℃)	-35	-35	-35	-35	-35	-35	-35	-35	-33	-33	-35	-35	--	0	0